

FLOOR COATINGS

Textured Epoxy Topcoat

Solvent-free epoxy topcoat producing an orange-peel textured finish. Plan the surface texture and layer thickness together with the application method. Request technical support for primer selection.

Packaging 24 kg set · A: 19 kg + B: 5 kg	Product name RENGA TX	Finish Gloss / orange-peel texture
Components Two-component	Density 1,55 ± 0,05 kg/L	Solids content 100% by weight
Pot life 30–35 minutes at 23 °C / 200 g	Consumption 500–600 g/m ²	Touch dry 6–8 hours at 23 °C
Recoat time 24 hours at 23 °C	Full cure 7 days at 23 °C	

Use and selection

Solvent-free epoxy topcoat producing an orange-peel textured finish. Plan the surface texture and layer thickness together with the application method. Request technical support for primer selection.

Before your project

Specify the substrate, existing coating and surface condition. Check preparation requirements and compatibility before application.

Share the area or line dimensions, intended use, application equipment and project specification, if available.

RAL 9016 · RAL 1023 · RAL 9017 · RAL 3020 · RAL 5015 · RAL 6001 · RAL 2004 · RAL 7040

Request the current technical data sheet and safety data sheet for the selected product and its components before application. Product brochures and catalogues do not replace these documents.

[Product information](#)