

ROAD MARKING PAINTS

MMA Screed Road Marking Material

Two-component MMA road marking material for screed application. The main component and hardener are supplied separately. Plan thickness and application method according to the project specification and current technical data sheet.

Packaging 25 kg main component · hardener supplied separately	Colour availability White and yellow ready; other colours made to order	Minimum order 1 tonne per colour
Hardener AKPEROX BP50 (powder)	Hardener packaging 25 kg carton	Mixing ratio 1–2% of the main component weight, depending on weather conditions
Pot life approx. 15 minutes at 20 °C	Application temperature (substrate) +5–40 °C	Opening to traffic 30–45 minutes after application
Density 1.70 ± 0.05 kg/L	Application thickness 2–5 mm	Shelf life 1 year
Standard TS EN 1871		

Use and selection

Two-component MMA road marking material for screed application. The main component and hardener are supplied separately. Plan thickness and application method according to the project specification and current technical data sheet.

Before your project

Specify the substrate, existing coating and surface condition. Check preparation requirements and compatibility before application.

Share the area or line dimensions, intended use, application equipment and project specification, if available.

RAL 9016 · RAL 1023 · RAL 9017 · RAL 3020 · RAL 5015 · RAL 6001 · RAL 2004 · RAL 7040

Request the current technical data sheet and safety data sheet for the selected product and its components before application. Product brochures and catalogues do not replace these documents.

[Product information z](#)